


AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:


1. (original): Process for the manufacture of a (meth)acrylate di-ammonium salt of formula (I)




(I)

wherein R^1 represents hydrogen or methyl, each R^2 , independently, represents an alkyl comprising from 1 to 4 carbon atoms, each R^3 , independently, represents an alkyl or an aralkyl and each X^- , independently, represents an anion, comprising

(1) the reaction of the di-amino (meth)acrylate of formula (II)



with at least one alkyl or aralkyl derivative of formula R_3X in an organic solvent containing at most 5000 ppm, preferably at most 1000 ppm, of water and wherein the compound of formula (I) has a solubility at 25 °C of less than 1 g/100 g of solvent, preferably of less than 0.5 g/100 g of solvent, and wherein the solubility of the corresponding amino-(meth)acrylate ammonium salt of formula (V)




has a solubility at 25 °C of at least 20 g/100 g of solvent ; and

(2) the separation of the compound of formula (I) from the reaction mixture without dissolving it in water, the compound of formula (I) being separated from the reaction mixture in the form of a

solid product comprising, per mole of the compound of formula (I), less than 0.1 mole, preferably less than 0.05 mole and more preferably less than 0.01 mole of the compound of formula (V).


2. (original): Process for the manufacture of a polymer comprising units derived from at least one (meth)acrylate di-ammonium salt of formula (I)




(I)

wherein R1 represents hydrogen or methyl, each R2, independently, represents an alkyl comprising from 1 to 4 carbon atoms, each R3, independently, represents an alkyl or an aralkyl and each X- , independently, represents an anion, comprising

(1) the reaction of the di-amino (meth)acrylate of formula (II)



with at least one alkyl or aralkyl derivative of formula R^3X in an organic solvent containing at most 5000 ppm, preferably at most 1000 ppm, of water and wherein the compound of formula (I) has a solubility at 25°C of less than 1 g/100 g of solvent, preferably of less than 0.5 g/100 g of solvent, and wherein the solubility of the corresponding amino-(meth)acrylate ammonium salt of formula (V)



has a solubility at 25°C of at least 20 g/100 g of solvent ;

(2) the separation of the compound of formula (I) from the reaction mixture without dissolving it in water ; the compound of formula (I) being separated from the reaction mixture in the form of a

solid product comprising, per mole of the compound of formula (I), less than 0.1 mole, preferably less than 0.05 mole and more preferably less than 0.01 mole of the compound of formula (V), and


(3) the polymerisation of at least the compound of formula (I) contained in said solid product to achieve said polymer.

3. (original): Process according to claim 2, wherein step (3) comprises the co-polymerisation of at least 12 % by weight, preferably of at least 20 % by weight, and more preferably of at least 25 % by weight of the compound of formula (I) contained in said solid product with at the most 88 % by weight, preferably at the most 80 % by weight, and more preferably at the most 75 % by weight of at least one further monomer, the compound of formula (I) being co-polymerised preferably in an amount of less than 99 % by weight, more preferably in an amount of less than 85 % by weight with said further monomer.

4. (currently amended): Process according to ~~claim 2 or 3~~, claim 2, characterised in that said process is a radical co-polymerisation of a water-based solution of monomers polymerised by emulsion or suspension techniques.

5. (currently amended): Process according to ~~any one of the claims 2 to 4~~, claim 2, wherein step (3) comprises the co-polymerisation of from 1 to 99 parts by moles of the

compound of formula (I) contained in said solid product with from 1 to 99 parts by moles of at least one acrylamide monomer of formula (VI)




wherein R5 is hydrogen or methyl, R6 and R7 are, independently, hydrogen, alkyl comprising from 1 to 6 carbon atoms, optionally substituted by one or more hydroxy or alkoxy groups.

6. (currently amended): Process according to ~~any one of the claims 1 to 5,~~claim 1, wherein the solvent is an aprotic dipolar solvent, in particular a solvent selected from the group consisting of acetone, methylethylketone, ethylacetate, nitromethane, acetonitrile or mixtures thereof, the solvent being preferably acetonitrile.


7. (currently amended): Process according to ~~any one of the claims 1 to 6,~~claim 1, wherein the separation of the (meth)acrylate di-ammonium salt of formula (I) from the reaction mixture is done by mechanical separation, in particular by filtration or centrifugation.

8. (currently amended): Process according to ~~any one of the claims 1 to 7,~~claim 1, wherein the reaction mixture obtained after step (2) is recycled.

9. (currently amended): Process according to ~~any of claims 1 to 8,~~ claim 1, wherein the di-amino (meth)acrylate of formula (II) used in step (1) is prepared by the transesterification of a 1,3-di-amino-2- propanol of formula (III)



wherein each R₂, independently represents an alkyl comprising from 1 to 4 carbon atoms, with a (meth)acrylate of formula (IV)



wherein R¹ represents hydrogen or methyl and R₄ represents an alkyl comprising from 1 to 4 carbon atoms, in the presence of a lithium-catalyst.

10. (currently amended): Process according to ~~any one of the preceding claims, claim 1,~~
wherein X is Cl.

11. Process according to ~~any one of the preceding claims, claim 1,~~ wherein the di-amino (meth)acrylate of formula (II) is allowed to react in step (1) with more than 2, preferably with more than 2.1, equivalents of said alkyl or aralkyl derivative of formula R3X.

12. (currently amended): Process according to ~~any one of the preceding claims, claim 1,~~ wherein the reaction of step (1) is effectuated in an amount of between 500 and 5000 g of solvent per mole of the di-amino (meth)acrylate of formula (II).

13. (currently amended): Solid ~~product obtainable~~ product, obtained by the process according to claim 1, ~~or by the process according to any one of the claims 6 to 12 when dependent on claim 1,~~ containing the (meth)acrylate di-ammonium salt of formula (I) and, per mole of this salt, less than 0.1 mole, preferably less than 0.05 mole and more preferably less than 0.01 mole, of the corresponding amino-(meth)acrylate ammonium salt of formula (V).


14. (currently amended): ~~Polymer obtainable~~ Polymer, obtained by the process according to any one of the claims 2 to 5, ~~or by the process according to any one of the claims 6 to 12 when dependent on any one of the claims 2 to 4,~~ claim 2, containing units derived from at least one

(meth)acryl di-ammonium salt of formula (I) and, per n units derived from this di-ammonium salt, less than $0.1 \cdot n$, preferably less than $0.05 \cdot n$ and more preferably less than $0.01 \cdot n$ units derived from at least one amino-(meth)acrylate ammonium salt of formula (V).


15. (currently amended): ~~Polymer obtainable~~ Polymer, obtained by the process according to claim 3, ~~or by the process according to any one of the claims 4 to 12 when dependent on claim 3,~~ containing at least 12 % by weight, preferably at least 20 % by weight, and more preferably at least 25 % by weight of units derived from at least one (meth)acryl di-ammonium salt of formula (I) and at the most 88 % by weight, preferably at the most 80 % by weight, and more preferably at the most 75 % by weight of units derived from at least one further monomer, the polymer containing preferably less than 99 % by weight, more preferably less than 85 % by weight of at least one (meth)acryl di-ammonium salt of formula (I).

16. (currently amended): Use of a polymer according to ~~claim 14 or 15~~ claim 14, as flocculant.


17. (original): Process for the manufacture of a di-amino (meth)acrylate of formula (II)



by transesterification of a 1,3-di-amino-2- propanol of formula (III)



wherein each R^2 , independently represents an alkyl comprising from 1 to 4 carbon atoms, with a (meth)acrylate of formula (IV)



wherein R¹ represents hydrogen or methyl and R⁴ represents an alkyl comprising from 1 to 4 carbon atoms, in the presence of a lithium-catalyst.

18. (currently amended): Process according to ~~claim 9 or 17,~~ claim 9, wherein the lithium catalyst is chosen from Li₂O, LiOCH₃, LiOH and their mixtures.

19. (currently amended): Process according to claim 9, ~~17 or 18,~~ wherein the transesterification is done at a temperature not exceeding 120 °C, preferably at a temperature not exceeding 110 °C, the transesterification being preferably done at a temperature of at least 80 °C.

20. (currently amended): Process according to ~~any one of the claims 1 to 12 or according to any one of the claims 17 to 19,~~ claim 1, wherein R¹ is methyl.

21. (currently amended): Process according to ~~any one of the claims 1 to 12 or according to any one of the claims 17 to 20,~~ claim 1, wherein R² is methyl.

22. (currently amended): Process according to ~~any one of the claims 1 to 12 or according to any one of the claims 17 to 21,~~ claim 1, wherein R³ is methyl.

23. (currently amended): Process according to ~~any one of the claims 1 to 12 or according to any one of the claims 17 to 21,~~ claim 1, wherein R3 is benzyl.

24. (currently amended): Process according to ~~any one of the claims 9 to 12 or according to any one of the claims 17 to 23,~~ claim 9, wherein R4 is methyl.